

# Technical Data Sheet

Sr.No: cpvc-003

## Chlorinated PVC Resin RJ5767

### Application

HEC's RZ5767 is a post-chlorinated-polyvinyl chloride resin(powder form) produced by the HEC's post chlorination process and the technology is introduced from France Arkema.

It can be used for-

- Injection molding of pressure fittings for hot water and industrial pipes
- Extrusion of pipes,profiles and sheets.

### Specification

ITEM	Unit	Index
Color	—	White
K-Value(PVC)	—	57
Chlorine Content	%	67.0-68.0
Number of Impurities	Number/100g	≤20
Bulk Density	%	0.65-0.73

### Package

25 kg      3 in 1 Composite kraft paper bag

Other packaging according to customer needs

# Technical Data Sheet

Sr.No: cpvc-003

---

## Storage/Shelf Life

The material must be stored in a dry place away from all heat sources, direct or indirect.

The recommended shelf life for this resin is 18 months maximum.

## Safety Hazards identification

More advice and information given in the safety data sheet.

## Disclaimer

This information and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to verify the information currently provided - especially that contained in our safety data and technical information sheets - and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery.

Hangzhou Electrochemical Group CO.,Ltd.  
Linjiang Industrial Park, Hangzhou, China  
[Http://www.hec-cn.com](http://www.hec-cn.com)

Tel +86 571 86617799-6731  
Fax +86 571 82988100  
[Email: hec571@hotmail.com](mailto:hec571@hotmail.com)